

Material		Properties
Silicone Rubber Sheet Grade GP 80 FDA Silicone – Elastomer: Vinylmethylsiloxan – VMQ – Peroxide cured Translucent.		Directives: EU1935/2004, 2023/2006; FDA 177.2600; (See also below)
Technical data		Applications
General Properties	Specification Limits (Typical Value)	The material is according to Reach and RoHS Silicone Rubber Sheet Grade GP 60 FDA is suitable for food, medical + pharmaceutical applications, physiological harmless, bacteriological indifferent, allergy uncommitted, fungicide, non-toxic, non corrosive, non sticky, nonconductive, repeated sterilization.
Hardness**	80Sh.A.	
Density*	1.2 g/cm ³	
Compression Set***	32% (22h / 175°C)	
Mechanical Properties		
Tensile Strength	10N/mm ²	
Elongation at break	420% (450%)	
Tear Strength	26N/mm	
Max. cont. Temperature	200°C	
Min. Temperature	-60°C	
Resistance: Excellent resistance to ozone, oxidant, ultraviolet light, corona discharge, cosmic radiation, (V10 ⁵ GRAYS/10 ⁷ RADS), ionising chemical. Conditionally oil-resistant dependent on type – self-testing.		
We confirm, that there are no banned substances in Silicone Rubber Sheet Grade 80 GP translucent and it does not contain any chemicals listed in the regulations: <u>IRLS-LIST 101 (prev. VDA-LIST 232-101); EU-Basic Directive 76/769/EWG,</u> <u>EU Directive: 91/157/EWG; 94/62/EG; 2000/53/EG; 2003/11/EG; 2003/11/EG; 2003/53/EG; 2004/01/EG;</u> <u>ROHs 2002/95/EG; WEEE 2002/96/EG; REACH EG Regulation 1907 – ECHA/PR/10021 dated 13.01.2010;</u> <u>SVHC free, Definition s.S.2, Appendix XIV</u>		
Disclaimer		Availability
The information given and, in particular, any parameters, should be used for guidance purpose only. The Company does not give any warranty that the product will be suitable for the use intended by the Costumer. We reserve the right to make alternations of the data and the properties of the material without notice		Colour: Translucent, Red Ion Oxide, White, Blue as well others on request. Thickness: From 0.3 – 10.0mm others on request

Rev.: 2012-12-19/BB

*DIN 53479 A

** DIN 53505 ASTM D2240

*** DIN 53717 Type II BS 903 pt A6 type B