

Material		Properties
PTEFE COATED GLASS FIBRE SELF-ADHESIVE WITH BACKING PAPER		Directives: EU1935/2004, 2002/7/EC, 2007/19EC, 2008/39/EC
Technical data		Applications
<b>General Properties</b>		<p>The material is according to Reach and RoHS</p> <p>This product, when used as the food contact surface of equipment in the preparation of food are in compliance with the Federal Food, Drug and Cosmetic Act, and the applicable Food Additive Regulations, including 21CFR, Section 177.1550</p> <p>The silicone adhesive does not apply to the above.</p>
Weight before Adhesive	455 g/m <sup>2</sup> +/-5%	
Thickness before adhesive	230µm	
PTFE percentage	55% +/-2%	
Adhesive Thickness	65 µm	
<b>Fabric &amp; Coating</b>		
Fabric material	Glass	
Coating	PTFE	
Adhesive (PSA)	Silicone	
<b>Mechanical Properties</b>		
Tensile Strength*	2000 N/5cm	
Max. cont. Temperature (PTFE)	260°C	
Max. cont. Temperature (adhesive)	180°C	
Min. Temperature	-70°C	
Disclaimer		Availability
<p>The information given and, in particular, any parameters, should be used for guidance purpose only.</p> <p>The Company does not give any warranty that the product will be suitable for the use intended by the Costumer.</p> <p>We reserve the right to make alternations of the data and the properties of the material without notice</p>		1000mm standard width

Rev.: 2012-11-13/51 0 (Z)BB

\*BS 3424 Part 4 Method 6